2025/2/19 10:34 2025/2/19 10:34

Experimental information

Inspection unit: LISUN GROUP

Inspection unit:

Inspection date: 2025/02/19 10:01:12
Inspection date: 2025/02/19 09:35:55

Experimenter: Zhang Rui

Remark:

Sample Information


Sample No.: 0219
Sample name: Leather
Sample volume: 0.0005g

Spectrum information

File name: 0219_Channel1.cws

File path: D:\Lisun\0219_Channel1.cws
Collection time: 2025-02-19 10:01:49

Analysis method: ROHS-4P



Test results table

No. Test	component name 1	Related components	Total area, tota	peak height, tot	al concentration test	based on test results	
	DIBP	DIBP	10.517 2.982 2	2.872415p		<50	Not detected
					pm		
2	DBP	DBP	40.515 3.769		105.048811	ÿ50&&ÿ500 qualified	
					ppm		
3	ВВР	BBP	10.175 2.829 2	5.189702p		<50	Not detected
0				,	pm		
4	DEHP	DEHP	38.825 6.133 8	5.409182p		ÿ50&&ÿ500 qualified	
					pm		